

AnyAddy®

(Methylcellulose)

Reference		FCC8 / JECFA / KFAC					
Grade		MC15	MC40M	MC15H	MC40H	MC50U	MC10T
Viscosity (cPs)	Label	15	400	1,500	4,000	50,000	100,000
	Range	12 ~ 18	300 ~ 560	1,125 ~ 2,100	3,000 ~ 5,600	37,500 ~ 70,000	75,000 ~ 140,000
pH		5.0 ~ 8.0					
Loss on drying (%)		NMT 5.0					
Residue on Ignition (Sulfated ash) (%)		NMT 1.5					
Lead (ppm)		NMT 2.0					
Cadmium (ppm)		NMT 1.0					
Mercury (ppm)		NMT 1.0					
Arsenic (ppm)		NMT 3.0					
Assay	Methoxyl groups (%)	27.5 ~ 31.5					

Revised 4.2 (2023-09-20)